



Alloy: **5A06**

Temper / Etat: F, O, H34 and etc.,

Mechanical Properties / Caracteristiques Mecaniques:

Temper/Etat	Tensile Strength (Rm/Mpa)	Yield Strength (Rp0.2/Mpa)	Elongation %
F			
O	> 315	> 155	16
H112	> 315*	> 155*	6—16*
H34	> 430	> 340	10—15

Width / Largeur Disponible:

Thickness < 10mm, Max. Width 1500mm

Thickness > 10mm, Max. Width 2400mm

Minimum Thickness / Epaisseur:

1 mm